



Daylight whites

PANAGET

manufacture française de parquet
DEPUIS 1929



No 1005924

FRENCH OAK CLASSIC LINEN, HERRINGBONE 90 TONGUE & GROOVE / 12 MM

Characteristics

Species: French oak **Origin:** France

Grading: **Classic** - light and dark wood, black knots, medular rays, discolouration.

Finish: **Linen** - brushed, light white matt lacquered / Ecostrong lacquer

While we take the greatest care in manufacturing our flooring, there can sometimes be slight variations in colouring. So it's important to factor in margin of 2-5% more than the actual surface you're covering. This means you won't run out of planks and you will be sure to enjoy a beautiful finished product.

Design

Engineered single plank, herringbone made under the patent EN 13489
Tongue & Groove



Description

Width: 90 mm

Length: 590 mm

Thickness: 12 mm

Top layer: 2.5 mm

Core: HDF*

Counterbalance: unrolled wood

Profile: 4 bevels

*High Density Fiber Board

Packing

Sqm/pack: 1.91

Pack/pallet: 32

Sqm/pallet: 61.12

Weight/sqm: 9.9 kg

Weight/pallet: 605.1 kg

Installation method



Floating glued
installation under the
patent DTU 51.11



Glue down installation
under the patent DTU 51.2



Floating installation using
plastic DPM and Isol 20 or fully
glue down using Presto PM



Fully glue down using
Presto PM



* Emissions of volatile substances which could be toxic if inhaled. These are rated on a scale from A+ (very low) to C (high).



DECLARATION OF PERFORMANCE

NO 1005924



Unique identification code of the product-type: Herringbone 90 Tongue & Groove, 12 mm, French oak

Intended use/es: Engineered single plank, herringbone made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: No4

Harmonised standard: EN 14342 : 2013

Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation	
Reaction to fire	Dfl-s1	EN 14342 : 2013	
Features for this classification: - Average minimum density (Kg/m ³) - Average thickness (mm) - Intended use, fitting mode	500 12 Floating fit		
Formaldéhyde emission	E1		EN 717-1
Content of pentachlorophénol	PCP ≤ 5 ppm		-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVP0910046A)	Classe A+ < 1µg/m ³	ISO 16000	
Breaking strength	N/A	-	
Slipperiness	N/A	-	
Thermal conductivity (W/m.K)	0.15	EN 14342 / Chapter 4.7	
Thermal resistance (m ² .K/W)	0.080		
Biological sustainability	Classe 1	EN 335	

N/A: Not Applicable

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1 and 2 category

The performance of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011. under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, 12 november 2019

Carole FRANÇOIS

