



Daylight whites

FRENCH OAK ZENITUDE LINEN, DIVA 184 CLICK / 12 MM

Characteristics

Species: French oak Origin: France

Grading: Zenitude - light and dark wood, black knots, filled knots, opened knots, discolouration, cracks, splits, sapwood. Grade with all pecularities of The wood without limitation. The size of The knots is proportional to The width of The planks.

Finish: Linen - brushed, light white matt lacquered / Ecostrong lacquer

While we take The greatest care in manufacting our flooring, there can sometimes be slight variations in colouring. So it's important to factor in margin of 2-5% more than The actual surface you're covering. This means you won't run out of planks and you will be sure to enjoy a beautiful finished product.

Design

Engineered extra-wide single plank made under The patent EN 13489 Click system made under Unilin patent NoEP1640530







Description

Width: 184 mm

Length: 495 to 1992 mm Thickness: 12 mm Top layer: 2.5 mm Core: HDF*

Counterbalance: unrolled wood

Profile: 4 bevels
*High Density Fiber Board

Packing

Sqm/pack: 2.20 Pack/pallet: 40 Sqm/pallet: 88.00 Weight/sqm: 9.9 kg Weight/pallet: 871.2 kg

Installation method



Glue-free floating installation under The patent DTU 51.11



Floating installation using plastic DPM and Isol 20 or fully glue down using Presto PM




Glue down installation under The patent DTU 51.2



Fully glue down using Presto PM







* Emissions of volatile substances which could toxic if inhaled. These are rated on a scale from









DECLARATION OF PERFORMANCENO 1007320

CE

Unique identification code of The product-type: Diva 184 Click, 12 mm, French oak **Intented use/es:** Engineered extra-wide single plank made under the patent EN 13489

Glue-free floating installation under The patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: No4

Harmonised standard: EN 14342: 2013

Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction to fire	Dfl-s1	
Features for this classification:		
- Average minimum density (Kg/m³)	500	EN 14342 : 2013
- Average thickness (mm)	12	
- Intented use, fitting mode	Floating fit	
Formaldéhyde emission	E1	EN 717-1
Content of pentachlorophénol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVP0910046A)	Classe A+ < 1µg/m³	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0.15	EN 14342 / Chapter 4.7
Thermal resistance (m ² .K/W)	0.080	
Biological sustainability	Classe 1	EN 335

N/A: Not Applicate

The performance of product identified above is in conformity with The set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011. under The sole responsability of The manufacturer identified above.

Signed for and behalf of The manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, 15 november 2019

Carole FRANÇOIS

^{*}VOC: Volatile Organic Compounds

^{**}CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1 and 2 category