



Timeless natural hues

PANAGET

manufacture française de parquet
DEPUIS 1929



No 1016745

FRENCH OAK CLASSIC/AUTHENTIC SATIN, HERRINGBONE 90 TONGUE & GROOVE / 12 MM

Caracteristics

Species: French oak **Origin:** France

Grade: Classic/Authentic - light and dark wood, black knots, filled knots, partially opened knots, medular rays, discolouration, black marks, cracks. The size of the knots is proportional to the width of the planks.

Finish: Satin - unbushed, satin lacquered / Ecostrong lacquer - Shine (gloss): 28/32

Design

Engineered single plank, herringbone made under the patent EN 13489
Tongue & Groove



Description

Width: 90 mm

Length: 590 mm

Thickness: 12 mm

Top layer: 2.5 mm

Core: HDF*

Counterbalance: unrolled wood

Profile: 4 bevels

*High Density Fiber Board

Packing

Sqm/pack: 1.91

Pack/pallet: 32

Sqm/pallet: 61.12

Weight/sqm: 9.9 kg

Weight/pallet: 605.1 kg

Installation method



Floating glued
installation under the
patent DTU 51.11





Glue down installation
under the patent DTU 51.2



Floating installation gluing T&G
using plastic DPM and Isol 20 or
fully glue down using Presto PM



Fully glue down using
Presto PM



PANAGET - 3 rue d'Orgères - 35230 Bourgarré - FRANCE
tel: +33 (0)2 99 05 77 77 // fax: +33 (0)2 99 57 73 55 // www.panaget.com

DECLARATION OF PERFORMANCE

NO 1016745



Unique identification code of the product-type: Herringbone 90 Tongue & Groove, 12 mm, French oak

Intended use/es: Engineered single plank, herringbone made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: No4

Harmonised standard: EN 14342 : 2013

Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction to fire	Dfl-s1	EN 14342 : 2013
Features for this classification: - Average minimum density (Kg/m ³) - Average thickness (mm) - Intended use, fitting mode	500 12 Floating fit	
Formaldéhyde emission	E1	
Content of pentachlorophénol	PCP ≤ 5 ppm	
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEV0910046A)	Class A+ < 1µg/m ³	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0.15	EN 14342 / Chapter 4.7
Thermal resistance (m ² .K/W)	0.08	
Biological sustainability	Class 1	EN 335

RE2020 - Building Carbon Index: 3 kg.CO₂/m²

French environmental regulation : it aims to reduce the carbon footprint of new buildings over their estimated 50-year life cycle.

FDES 2022 - Life Cycle impact assessment: 8.6 kg éq. CO₂/m²

N/A : Not Applicable

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, 16 december 2021

Carole FRANÇOIS

3 rue d'Orgères - 35230 Bourgbarré - FRANCE / tel: +33 (0)2 99 05 77 77 - fax: +33 (0)2 99 57 73 55

Entreprise dont le système qualité a été **certifié ISO 9001** par Bureau Veritas Certification.

SAS au capital de 4 957 200 € - RCS Rennes B 402 853 220 - Siret : 402 853 220 000 34 - APE : 1622 Z - No TVA : FR 0640 2853220

www.panaget.com